

# इंटरनेट

# मानक

## Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”


IS 11014-2 (1984): Piezoelectric Ceramic Materials, Part 2: Types 1 and 5 [LITD 5: Semiconductor and Other Electronic Components and Devices]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”



BLANK PAGE



Indian Standard

SPECIFICATION FOR  
PIEZOELECTRIC CERAMIC MATERIALS

PART 2 TYPES 1 AND 5

0. General — This standard ( Part 2 ) shall be read in conjunction with IS : 11014 ( Part 1 )-1984 'Specification for piezoelectric ceramic materials: Part 1 General aspects and methods of measurements'.

1. Type Designation — See 3 of IS : 11014 ( Part 1 )-1984.

1.1 Type 1 — Modified barium titanate materials having relatively high frequency constant ( $N_3t$ ) and suitable for low signal application.

1.2 Type 5 — Modified lead zirconate titanate materials having high planar coupling coefficient ( $k_p$ ) and suitable for general purpose low signal application, for example ultrasonic transducers.

2. Test Specimens — In general, practical dimensions used in ceramic elements may not be suitable for the measurement of many parameters. To determine these parameters accurately, it is essential to have test specimen of three different configurations as follows:

- a)  $l \geq 2.5 w, t, D$  or
- b)  $l \geq 3.5 w, t$  or
- c)  $D \geq 10 t$

where

$l$  = length,  $w$  = width,  $t$  = thickness, and  $D$  = diameter of the disc.

3. Parameters — See Table 1 below:

TABLE 1 PARAMETERS WITH TOLERANCE FOR PIEZOELECTRIC CERAMIC MATERIALS  
TYPES 1 AND 5

SI No.	Parameters	Symbols	Piezoelectric Materials Types		
			Type 1	Type 5	Tolerance
(1)	(2)	(3)	(4)	(5)	(6)
					Percent
I)	Density ( $M/n$ ) ( $10^3 \text{ kg/m}^3$ )	$d$	5.6	7.6	—
II)	Dielectric constant	$K_s^T$	1 300	1 700	20
III)	Dissipation factor ( $Max$ )	$\tan \delta$	$\geq 0.025$	$\geq 0.025$	—
iv)	Resistivity ( $\Omega \text{ cm}$ )	$\rho$	$\sim 10^{12}$	$\sim 10^{13}$	—
v)	Planar coupling co-efficient	$K_p$	0.33	0.55	$\pm 5$
vi)	Piezoelectric charge constant $\times 10^{-18} \text{ C/N}$	$d_{33}$	2 145	350	$\pm 10$
vii)	Piezoelectric voltage constant $\times 10^{-3} \text{ — m/N}$	$g_{33}$	12.7	24	$\pm 10$
viii)	Frequency constant (Hz)	$N_3t$	2 700	1 900	$\pm 10$
ix)	Mechanical quality factor	$Q_m$	200	85	$\pm 10$
x)	Curie temperature ( $^{\circ}\text{C}$ )	$\theta_c$	120	280	—

Adopted 28 September 1984

© December 1984, ISI

Gr 1